


38

REQUEST OF EARLY NOTIFICATION OF SERIAL NUMBER

Inventor(s): Takayuki USUI and Tokiichi MASUDA

Title: PLANOGRAPHIC PRINTING PLATE PACKAGING
MATERIAL AND PLANOGRAPHIC PRINTING PLATE
PACKAGING STRUCTURE



Atty Doc. #: Q61689 Client: TAIYO, NAKAJIMA & KATO

Filing Date: February 21, 2001 # Pgs. Spec/Abst: 32/1 #Claims: 18

Dwg. Sheets: 4 Decl YES Prelim Amdt NO
PTO form 1449 w/refs PTO form 1595 \$ 790.00
IDS/Prior Art: YES Pr Doc: YES(2) Asgmt: YES Fee: 40.00

☒ Check Attached ☐ Charge to Deposit # 19-4880 Atty/Sec: DM/aaa

SERIAL NO.

CONF NO.

RECEIVED
NOV -5 2002
TC 1700 MAIL ROOM



PATENT APPLICATION

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re application of

Takayuki USUI, et al.

Appln. No.: 09/788,351

Confirmation No.: 1061

Filed: February 21, 2001

For: PLANOGRAPHIC PRINTING PLATE PACKAGING MATERIAL AND
PLANOGRAPHIC PRINTING PLATE PACKAGING STRUCTURE

Docket No: Q61689

Group Art Unit: 1772

Examiner: Walter AUGHENBAUGH

RECEIVED
NOV -5 2002
TC 1700 MAIL ROOM

AMENDMENT UNDER 37 C.F.R. § 1.111

Commissioner for Patents
Washington, D.C. 20231

Sir:

In response to the Office Action dated July 3, 2002, please amend the above-identified application as follows:

IN THE SPECIFICATION:

Please delete the paragraph bridging pages 23 and 24 and insert therefor:

Further, in the second embodiment, Bekk smoothness of the contacting portion (a portion contacting the coating film) of the piece of protection cardboard 32 is between 3 seconds and 900 seconds as the contacting portions of the interleaf sheets 14 of the first embodiment. Therefore, in the second embodiment, film peeling is also prevented in such a case in which the piece of protection cardboard 32 and the coating film are rubbed by each other, for example, during transportation or the like. Particularly, when a piece of the protection cardboard 32 with a contacting portion having Bekk smoothness between 3 seconds and 100 seconds or between 250 seconds and 900 seconds is used, film peeling of the planographic printing plates 10 is prevented regardless of types of the planographic printing plates 10.